

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
14 July 2005 (14.07.2005)




PCT

(10) International Publication Number  
**WO 2005/064733 A1**

- (51) International Patent Classification<sup>7</sup>: **H01M 10/40**, 10/39, 10/36, 6/14, 6/16, H01G 9/02
- (71) Applicant (for CA only): **SHELL CANADA LIMITED** [CA/CA]; 400-4th Avenue S.W., Calgary, Alberta T2P 2H5 (CA).
- (21) International Application Number: **PC/T/EP2004/053182**
- (72) Inventors; and  
(75) Inventors/Applicants (for US only): **BEST, Adam** [AU/NL]; Julianalaan 136, NL-2628 NL Delft (NL). **LANDHEER, Hiske** [NL/NL]; Julianalaan 136, NL-2628 NL Delft (NL). **OOMS, Franciscus Güntherus Bernardus** [NL/NL]; Julianalaan 136, NL-2628 NL Delft (NL).
- (22) International Filing Date:  
30 November 2004 (30.11.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
03104985.1 29 December 2003 (29.12.2003) EP
- (71) Applicant (for all designated States except CA, US): **SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V.** [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,

[Continued on next page]

(54) Title: **ELECTROCHEMICAL ELEMENT FOR USE AT HIGH TEMPERATURES**



(57) Abstract: An electrochemical element for use at a high temperature has an anode, a cathode comprising an intercalation material having an upper reversible potential-limit of at most 4 V versus Li/Li<sup>+</sup> as active material, and an electrolyte arranged between the cathode and anode, which electrolyte comprises an ionic liquid with an anion and a cation comprising a pyrrolidinium ring structure having four Carbon atoms and one Nitrogen atom. Experiments revealed that rechargeable batteries comprising such an intercalation material and N-R<sub>1</sub>-N-R<sub>2</sub>-pyrrolidinium, wherein R<sub>1</sub> and R<sub>2</sub> are alkyl groups and R<sub>1</sub> may be methyl and R<sub>2</sub> may be butyl or hexyl, are particularly suitable for use at a temperature of up to about 150 degrees Celsius and may be used in oil and/or gas production wells.



TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LU, MC, NL, PL, PT, RO, SE,

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

## ELECTROCHEMICAL ELEMENT FOR USE AT HIGH TEMPERATURES

BACKGROUND OF THE INVENTION

This invention relates to an electrochemical element for use at high temperatures.

Electrochemical elements comprise a cathode and an anode,  
5 and an electrolyte which is arranged between the cathode and the anode. The cathode and anode generally comprise metallic current collectors and an active material, which can be the current collector material itself. An  
10 electrochemical cell that produces electricity as a result of a spontaneous chemical reaction is called a galvanic cell. An electrochemical element or cell in which a non-spontaneous chemical reaction is driven by an external current source is called an electrolytic cell.

An electrolyte is a compound, or combination of  
15 compounds, capable of conducting electricity in the form of an ionic current, carried by mobile ions. Examples of an electrolyte are a salt, or a mixture of salts, in its solid or molten state or dissociated into its ions in a solvent in which the solvent is not or only slightly  
20 dissociated.

Electrochemical elements may be configured as a primary battery or a rechargeable battery or an electrochemical capacitor. Rechargeable batteries are often referred to as secondary batteries and non-  
25 rechargeable batteries are often referred to as primary batteries.

A battery is a device that stores electrical energy using one or more electrochemical cells. The cells can be connected in series or parallel. The physical

construction of a cell is such that a direct reaction of the chemicals stored in the electrodes is prohibited by physically separating the electrodes by an electrolyte. When the two electrodes are connected through an external circuit, a galvanic cell will produce an electrical current. Electrons will flow through the external circuit, ions will flow through the electrolyte.

The reactions at the electrodes, involving transfer of electrons from one substance to another and thus the reduction and oxidation of the substances, are called redox reactions. The electrode where oxidation takes place is called the anode, the electrode where reduction takes place is called the cathode.

A rechargeable battery is a battery or electrochemical cell in which the chemical reaction, producing the electrical current upon discharge, is easily chemically reversible. A rechargeable battery can be recharged by applying an electrical current to its electrodes or terminals. Preferably, a rechargeable battery can be recharged hundreds of times without significant loss of storage capacity. A primary battery can be discharged only once and has to be disposed off afterwards.

The active material of the positive electrode in a primary battery will be reduced in the discharge process and is therefore also known as the cathode material. Vice versa is material at the negative electrode known as the anode material. The same naming convention is used for the active materials of a rechargeable battery in its charged state (a galvanic cell).

Batteries are widely used as a source of electrical energy for a variety of applications. Rechargeable batteries are used for many applications to avoid the

replacement and disposal of primary batteries. Moreover, their use allows the remote operation of devices in difficult to reach locations where exchange of primary batteries is not practically possible but where  
5 recharging a battery would be feasible. An example of such a location is in a wellbore for oil and gas production. Not only are downhole locations difficult to reach, the environmental conditions are also harsh with temperatures in the range of 60 to 200 °C which demands  
10 an electrochemical element suitable for high temperatures.

Most batteries are configured for use in a specified temperature range, which is typically capped due to instability, disintegration, melting and/or evaporation  
15 of the chemical compounds in the battery above a certain temperature. A typical operating range for batteries is between -40 and +60 °C.

Many rechargeable battery chemistries have been developed. Examples are Lead-acid, Nickel-Cadmium,  
20 Nickel-metalhydride, and Lithium (Lithium-metal and Lithium-ion) batteries. From these, batteries based on Lithium chemistry are most interesting since they offer the highest energy density because Lithium has the lowest reduction potential known (-3.045 V versus a standard  
25 hydrogen electrode) and has a high specific storage capacity of 3828 mAh/g (for a Lithium 7 isotope=<sup>7</sup>Li). However, the formation of Lithium dendrites on the Lithium anode in rechargeable batteries with electrolytes based on organic solvents has been a safety concern. This  
30 has led to the development of Lithium-ion batteries (Li-ion) in which the Lithium anode has been replaced with an intercalation material.

An intercalation or insertion compound is a host compound in which a guest species can be stored or from which it can be extracted. Examples of three dimensional intercalation materials are  $\text{LiMn}_2\text{O}_4$  and  $\text{Li}_4\text{Ti}_5\text{O}_{12}$  which  
5 reversibly allow the extraction and/or insertion of Lithium ions as guest species from/in their cubic crystal lattice structures.

An intercalation-reaction or insertion-reaction is defined as a reaction, generally reversible, that  
10 involves the introduction or removal of a guest species into or from a host structure without a major structural modification of the host. In the strictest sense, intercalation refers to the insertion of a guest into a two-dimensional host; however, the term also now commonly  
15 refers to one-dimensional and three-dimensional host structures. An example is the insertion of Lithium into layered  $\text{TiS}_2$ :  $x \text{ Li} + \text{TiS}_2 \rightarrow \text{Li}_x\text{TiS}_2$  ( $0 \leq x \leq 1$ ) (this example is described in the IUPAC Compendium of Chemical Terminology, 2nd Edition, 1997). Here,  $x$  is the variable  
20 amount of Lithium intercalated in  $\text{TiS}_2$ . The given limits ( $0 \leq x \leq 1$ ) indicate the compositional range over which  $x$  can be varied in a reversible way. Between these limits,  $\text{Li}_x\text{TiS}_2$  exhibits a specific potential curve as function of  $x$  when measured versus a suitable reference electrode,  
25 which is Lithium metal in case of Lithium intercalation. Many reversible intercalation materials are known, each having a specific potential curve associated with a specific reversible composition range ( $x_{\min} \leq x \leq x_{\max}$ ). These potential curves can be characterised by a lower-  
30 and an upper reversible-potential-limit ( $\text{RPL}_{\text{low}}$  and  $\text{RPL}_{\text{upp}}$ , respectively) and an average potential  $V_{\text{avg}}$ . Some examples are given in table 1.

Table 1. Intercalation materials with reversible composition range and associated capacity,  $RPL_{low}$ , average-potential, and  $RPL_{upp}$  versus  $Li/Li^+$ . Potentials for  $Mg_xMo_3S_4$  are versus  $Mg/Mg^{2+}$ .

Material	$(x_{min} \leq x \leq x_{max})$	C (Ah/kg)	$RPL_{low}$ (V)	$V_{avg}$ (V)	$RPL_{upp}$ (V)
$Li_{1+x}CrTiO_4$	$0 \leq x \leq 1$	157	1.0	1.5	2.0
$Li_{4+x}Ti_5O_{12}$	$0 \leq x \leq 3$	175	1.05	1.55	2.05
$Li_{4+x}Mn_5O_{12}$	$0 \leq x \leq 3$	161	2.4	2.9	3.3
$Li_xTiS_2$	$0 \leq x \leq 1$	240	1.5	2.1	2.5
$Li_{1+x}Ni_{0.5}Mn_{1.5}O_4$	$0 \leq x \leq 1$	146	2.5	2.9	3.3
$Li_{1+x}Mn_2O_4$	$0 \leq x \leq 1$	148	2.5	2.9	3.3
$Li_{1-x}FePO_4$	$0 \leq x \leq 1$	160	3.0	3.4	3.8
$Li_{1-x}Mn_2O_4$	$0 \leq x \leq 0.8$	120	3.5	4.1	4.2
$Mg_xMo_3S_4$	$0 \leq x \leq 1$	120	0.2	1.1	2.0

The potentials measured versus  $Mg/Mg^{2+}$  can easily be converted to potentials versus  $Li/Li^+$  by using the known reduction potentials versus the standard hydrogen electrode (SHE):  $Li^+ + e = Li$  -3.045 V and  $Mg^{2+} + 2e = Mg$  -2.375 V. This means that the upper cut-off potential of  $Mg_xMo_3S_4$  of 2.0 V versus  $Mg/Mg^{2+}$  becomes 2.67 V versus  $Li/Li^+$ .

In the field of batteries, it is common to use so called lower- and upper cut-off potentials. These do not necessarily coincide with the RPL potentials of the active materials used. The cut-off potentials are a means of controlling the composition of the intercalation material in a battery and determine the utilisation of

the storage capacity. Setting the cut-off potentials to a window wider than the window defined by the RPL values may result in the irreversible oxidation or reduction of the active materials and/or the electrolyte, leading ultimately to failure of the battery. Setting the cut-off potentials to a window smaller than the RPL window results in a lower utilisation of the storage capacity of the active materials, but in general leads to a longer battery life. The current state-of-the-art Lithium and Li-ion batteries comprise positive electrode (cathode) materials like  $\text{MnO}_2$ ,  $\text{LiCoO}_2$ ,  $\text{LiNi}_{0.8}\text{Co}_{0.2}\text{O}_2$ , and  $\text{LiMn}_2\text{O}_4$ . Carbonaceous materials like graphite, MCMB, and petroleum coke are used as negative (anode) materials in Li-ion batteries. Batteries made by a combination of such cathode and anode materials show attractive high voltages between 3 and 4 V.

The electrolytes used in these batteries are based on Lithium salts as for example  $\text{LiPF}_6$ ,  $\text{LiBF}_4$ ,  $\text{LiClO}_4$ , and  $\text{LiAsF}_6$  dissolved in (mixtures of) organic solvents like for example ethylene-carbonate (EC), di-methyl-carbonate (DMC), propylene-carbonate (PC), ethyl-methyl-carbonate (EMC) etc. These solvents are flammable and show considerable vapour pressures at temperatures above 60 °C. Furthermore, these electrolytes can strongly react with the other battery components if the battery temperature rises above 60 °C, for example in the case of over-charging or internal shorting, imposing a potential danger. The operating temperature range is therefore limited from about -40 °C to +80 °C, which is similar to that found for the aqueous electrolytes.

Rechargeable battery chemistries that are able to operate at higher temperatures can be found in the molten



salt systems, for example the system Li//FeS<sub>2</sub> which, depending on the composition of the electrolyte, operates between 350 and 550 °C, or the system Na//S which operates between 220 and 350 °C. Therefore, there is a gap in the operating temperature range of current rechargeable battery technology between about 80 and 220 °C. The reason for this gap lies in the inadequate thermal properties of the available electrolytes.

The current technology of primary batteries, however, does not show such a temperature gap. The system Li//SO<sub>2</sub>Cl operates between -40 and +150 °C or, by alloying Lithium with Magnesium, between 70 to 200 °C. In this battery chemistry the electrolyte is the in-situ reaction product when Lithium metal contacts SO<sub>2</sub>Cl.

International patent application WO 01/15258 (D.R. MacFarlane et al.) discloses a solid-state conductive material comprising a pyrrolidinium or other cation. It further discloses that an anode of a Lithium battery may comprise a Lithium intercalation material.

Recent advances in the research of so called ionic liquids have shown that these materials have very promising properties to be used for a new generation of battery electrolytes, especially for high temperature batteries. Ionic liquids are known and have gained a lot of attention for their suitability in green chemistry. In contrast to the organic solvents, ionic liquids are non-flammable, non-volatile, and are chemically stable over a wide temperature range, up to 400 °C. Furthermore, they can be mixed with a wide range of electrolyte salts, allowing very high electrolyte salt concentrations. The conductivities of these electrolytes is comparable or sometimes higher than comparable organic solvent based

systems. Many of the ionic liquids are in their liquid state in a wide temperature range, starting below room temperature and ranging up to about 400 °C.

5 An article by D.R. MacFarlane, et al., (Journal of Phys. Chem. B, 103 (20) 1999, 4164) discloses that, among the known ionic liquids, some members of the pyrrolidinium family of ionic liquids show the widest electrochemical stability windows of up to 5.5 V, measured between glassy-carbon electrodes at 25 °C. The  
10 electrolyte stability window is the potential range, bounded by an oxidation- and a reduction-potential, in which the electrolyte is not oxidised nor reduced.

It is known for organic-solvent based electrolytes that a wider stability window is found when inert  
15 electrodes are used, like glassy-carbon or Platinum, than when electrodes containing active materials are used, like intercalation compounds. In that case, smaller electrolyte stability windows are found due to interaction of the electrolyte with the active materials.  
20 Furthermore, increasing the temperature enhances these interactions, resulting in an even smaller stability window. The large stability window of the pyrrolidinium based ionic liquids renders them as especially interesting for the application in electrolytes for use  
25 at high temperatures.

It is known that ionic liquids may be used as an electrolyte in electrochemical elements if an electrolyte salt (e.g. a Lithium salt) is added to the ionic liquid in order to obtain ionic conductivity of the required  
30 ion. The term ionic liquid is not well defined in literature but refers in general to a molten salt or to a liquid which consists of fully or almost fully dissociated ions. Room temperature ionic liquids are thus

ionic liquids that are in the liquid state at room temperature. 'Room temperature' is often defined as a temperature close to 25 °C but can be as high as 80 °C. It has to be noted therefore that not all compounds  
5 classified as 'ionic liquids' in the open literature have a melting point below 80 °C.

In this specification and claims ionic liquids are defined as 'ionic compounds', which are liquid in the operating temperature range. An ionic liquid may comprise  
10 a liquid mixture of ionic compounds.

It is known that in electrochemical elements that are configured for use at temperatures below 60 °C the electrolyte layer may comprise an extensive range of materials with ionic conductivity, such as electrolyte  
15 solutions comprising salts, which are dissociated into ions when dissolved in a solvent.

US patent 5,827,602 (Covalent Associates, Inc.) discloses the hydrophobic ionic liquids based on cations comprising pyridinium, pyridazinium, pyrimidinium,  
20 pyrazinium, imidazolium, pyrazolium, thiazolium, oxazolium, and triazolium. Also disclosed is the use of these ionic liquids in an electrochemical cell or a capacitor. No evidence of a stable functioning rechargeable battery incorporating these ionic liquids is  
25 shown and no operating temperature range is claimed.

US patent 5,965,054 (Covalent Associates, Inc.) discloses the use of the hydrophobic ionic liquids based on cations comprising pyridinium, pyridazinium,  
30 pyrimidinium, pyrazinium, imidazolium, pyrazolium, thiazolium, oxazolium, and triazolium in an electrolyte with a salt dissolved in a polar organic liquid or dissolved in liquid sulfur dioxide. The use of a polar solvent renders the known electrolyte not suitable for

high temperature applications due to vapour formation. No evidence of a stable functioning rechargeable battery incorporating these ionic liquids is shown and no operating temperature range is claimed.

5 US patent 6,326,104 (Electrochemical Systems, Inc.) discloses the use of electrolytes based on ionic liquids comprising the pyrazolium cation. This prior art reference provides four examples related to Lithium  
10 rechargeable batteries (a  $\text{LiMn}_2\text{O}_4$  cathode and a Lithium metal anode), wherein one cell was tested at 55 °C and three cells were tested at room temperature. All cells showed lower than expected capacities and/or fading, i.e. only an indication is given of the potential use. Also, a description was given that the following ionic liquids  
15 were not stable against metallic Lithium: 1-ethyl-3-methyl-imidazolium-tetrafluoroborate and 1,2-dimethyl-3-propylimidazolium-tetrafluoroborate.

US patent 5,855,809 (Arizona Board of Regents) discloses the use of electrolytes based on the following  
20 ionic liquids:  $\text{X}_3\text{PNPOX}_2$ ,  $\text{X}_3\text{PNCH}_3$ ,  $\text{X}_3\text{PNSO}_2\text{X}$ ,  $\text{XSO}_2\text{CH}_3$ ,  $\text{CH}_3\text{COX}$ , and  $\text{CH}_3\text{CH}_2\text{NPX}_3$  where X is a halogen atom. The results of one battery test are shown for a cell comprising a  $\text{LiMn}_2\text{O}_4$  cathode and a Lithium metal anode with 0.3 $\text{LiAlCl}_4$  in 0.7( $\text{AlCl}_4^-/\text{SO}_2\text{NPCl}_3^+$ ) as the  
25 electrolyte. However, FIG 16 in this patent is not showing the known voltage profile as function of x for a cell with a  $\text{Li}_x\text{Mn}_2\text{O}_4$  ( $0 \leq x \leq 1$ ) cathode and a Lithium metal anode. Moreover, the charge capacity is twice the discharge capacity which means that the efficiency is  
30 poor. It was further indicated that this cell behaviour was reversible over 50 cycles.

US patent 6,552,843 (Innovative Technology Licensing LLC) discloses a reversible electrodeposition device for controlling the propagation of electromagnetic radiation comprising an electrolyte based on ionic liquids  
5 comprising a cation based on *N*-methyl-pyrrolidinium, pyrrolidinium, 1-ethyl-3-methyl-imidazolium, 1-*N*-butyl-pyridinium, 2-methyl-1-pyrrolinium or 1-ethyl-imidazolium. A reversible electrodeposition device is an electrochemical device that can only operate as an  
10 electrolytic cell. Furthermore, the electrodes do not contain intercalation materials.

International patent application WO 02/063073 (B.R. Mattes, W. Lu) discloses the use of ionic liquids in electrochemical devices with conjugated polymers as  
15 the active materials in the electrodes. The cation of the ionic liquid is based on pyridinium, pyridazinium, pyrimidinium, pyrazinium, imidazolium, pyrazolium, thiazolium, oxazolium, triazolium, ammonium, pyrrolidinium, pyrrolinium, pyrrolium, and piperidinium.  
20 Conjugated polymers are polymer materials with alternating single and double bonds along the polymer chain. No battery related data are disclosed in this prior art reference.

Electrochemical elements for use at a temperature  
25 above +60 °C are known from International patent applications WO 0180344 and WO 0209215. The known electrochemical elements comprise a granular electrolyte layer, which is substantially free of polymer binder materials that would evaporate at an elevated  
30 temperature. A disadvantage of the use of a granular electrolyte layer is that the physical contact surfaces between the granules are relatively small, which results in a limited transfer of ions via the granules between

the cathode and anode, and in a moderate electric power output of the element. The batteries known from these prior art references are suitable for use at a temperature up to about 100 °C and have a limited output of electric power, which is expected to be a result of the limited contact areas between the solid state particles in the electrolyte.

International patent application WO2004/082059 discloses various pyrrolidinium based room temperature ionic liquids for use in energy storage devices, such as secondary lithium batteries.

The referenced prior art shows that ionic liquids can be used to make electrolytes.

Applicant now has discovered that only certain combinations of active materials and electrolytes comprising a pyrrolidinium based ionic liquid result in reversibly operating rechargeable batteries, especially at temperatures between 60 and 150 °C.

It is an object to provide an electrochemical element which is suitable for use at a high temperature.

It is a further object of the present invention to provide an electrochemical element which is suitable for use as a rechargeable battery, which can be used as an efficient energy source at a temperature above 50 °C, in particular in the range from 60 to 150 °C.

It is a further object of the present invention to provide a method for generating electrical energy by means of a rechargeable battery in an underground wellbore, such as an oil or gas production well, in which the temperature may be between 60 and 200 °C or a geothermal well in which the temperature may be up to several hundred degrees Celsius.

SUMMARY OF THE INVENTION

The electrochemical element according to the invention comprises a cathode, an anode and an electrolyte arranged between the cathode and anode, which electrolyte comprises an ionic liquid comprising an anion and a cation, which cation comprises a pyrrolidinium ring structure; and wherein the active material of the cathode comprises an intercalation material having an upper reversible-potential-limit of at most 4 V versus Li/Li<sup>+</sup>.

Applicant has discovered that intercalation materials with an upper reversible-potential-limit of more than 4 V versus Li/Li<sup>+</sup> are not suitable for reversible use. It is believed that the interaction between the electrolyte and these materials cause degradation of the materials and/or electrolyte resulting in loss of capacity, especially when used at temperatures above 70 °C.

Suitable intercalation materials with an upper reversible-potential-limit of at most 4 V are for example: LiFePO<sub>4</sub>, Li<sub>3</sub>Fe<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>, Li<sub>4</sub>Mn<sub>5</sub>O<sub>12</sub>, Li<sub>2</sub>Mn<sub>4</sub>O<sub>9</sub>, MnO<sub>2</sub>, FeS<sub>2</sub>, LiV<sub>3</sub>O<sub>8</sub>, V<sub>2</sub>O<sub>5</sub>, TiS<sub>2</sub>, TiO<sub>2</sub>, Li<sub>2</sub>Ti<sub>3</sub>O<sub>7</sub>, LiTi<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>, NaTi<sub>2</sub>(PO<sub>4</sub>)<sub>3</sub>, TiP<sub>2</sub>O<sub>7</sub>, LiV<sub>2</sub>O<sub>4</sub>, Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub>, LiCrTiO<sub>4</sub>, LiTi<sub>2</sub>O<sub>4</sub>, CuO, MgMo<sub>3</sub>O<sub>4</sub>, Li<sub>3</sub>FeN<sub>2</sub>, Li<sub>7</sub>MnN<sub>4</sub>. Particularly suitable intercalation materials are LiFePO<sub>4</sub>, Li<sub>4</sub>Mn<sub>5</sub>O<sub>12</sub>, TiS<sub>2</sub>, Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> and LiCrTiO<sub>4</sub>.

It is observed that WO 01/15258 discloses a solid-state conductive material comprising a pyrrolidinium or other cation. It further discloses that an anode of a Lithium battery may comprise a Lithium intercalation material.

It is believed that a solid-state conductive material has a lower ionic conductivity than an ionic liquid. The use of an ionic liquid in the electrochemical element

according to the present invention instead of a solid-state conductive material will result in a higher power density and therefore in a better performance of the electrochemical element.

5       When used in this specification and claims an active intercalation material is defined as an intercalation material that takes part in the redox reaction in the electrodes.

10       As an alternative to the use of an active intercalation material the anode of an electrochemical element may comprise a conjugated polymer. International patent application WO/02/063073 discloses an electrochemical element with an anode or cathode comprising a conjugated polymer as the major constituent  
15       of the active material.

20       The electrochemical element according to the invention may be configured for use as a primary or a rechargeable battery or an electrochemical capacitor at high temperature, such as a temperature above 50 °C and particularly at a temperature between 60 and 150 °C. It is furthermore preferred that the pyrrolidinium ring structure has the formula:  $N-R_1-N-R_2$ -pyrrolidinium, wherein  $R_1$  and  $R_2$  are alkyl groups and that  $R_1$  is methyl and  $R_2$  is butyl or hexyl.

25       The anion of the ionic liquid preferably comprises any of the following compounds:

-  $ClO_4^-$ ,  $AsF_6^-$ ,  $PF_6^-$ ,  $BF_4^-$ , a halogen ion,  $N(CF_3)_2^-$ ,  $N(CF_3SO_2)_2^-$  ('TFSI'),  $CF_3SO_3^-$ , and  $N(CH_3SO_2)_2^-$ ,  $N(C_2F_5SO_2)_2^-$ ,  $B(C_2O_4)_2^-$ ,  $C(CF_3SO_2)_3^-$ .



It is also preferred that the alkali salt comprises a Lithium salt which may comprise any of the following compounds:

- 5     -  $\text{LiN}(\text{CF}_3\text{SO}_2)_2$  ('LiTFSI'),  $\text{LiCF}_3\text{SO}_3$ ,  $\text{LiClO}_4$ ,  $\text{LiBF}_4$ ,  
     $\text{LiPF}_6$ , and  $\text{LiAsF}_6$ ,  $\text{LiB}(\text{C}_2\text{O}_4)_2$ ,  $\text{LiC}(\text{CF}_3\text{SO}_2)_3$ .

Alternatively the salt may comprise  $\text{MgCF}_3\text{SO}_2$  or  $\text{Mg}(\text{ClO}_4)_2$ .

10     The cathode suitably comprises  $\text{Li}_4\text{Ti}_5\text{O}_{12}$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ),  $\text{LiCrTiO}_4$ ,  $\text{V}_2\text{O}_5$ ,  $\text{TiS}_2$ ,  $\text{Li}_4\text{Mn}_5\text{O}_{12}$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Mn}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ) or  $\text{Li}_{1-y}\text{M}_y\text{FePO}_4$ , where  $\text{M} = \text{Mg}$ ,  $\text{Nb}$ ,  $\text{Zr}$ ,  $\text{Ti}$  or  $\text{Al}$  ( $0 \leq y \leq 0.02$ ), as the active material and as the major constituent by mass.

    The anode suitably comprises Lithium,  $\text{Li}_4\text{Ti}_5\text{O}_{12}$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ),  $\text{LiCrTiO}_4$ , as the active material.

15     The invention also provides a method of providing electrical energy in an underground wellbore, wherein the energy is provided by an electrochemical element according to the invention. The underground wellbore may form part of an oil and/or gas production well or a  
20     geothermal well.

#### BRIEF DESCRIPTION OF THE DRAWINGS

    The invention will be described in more detail with reference to the accompanying drawings wherein:

25     FIG. 1 A,B and C depict three examples of pyrrolidinium cations comprising a ring structure of four Carbon atoms and one Nitrogen atom;

    FIG. 2 is a graph showing charge and discharge capacity of the cell with a  $\text{Li}_4\text{Ti}_5\text{O}_{12}$  cathode and a Lithium metal anode 110 °C with LiTFSI in  $\text{P}_{14}\text{TFSI}$  in the  
30     molar ration 0.38:0.62. The capacity is given as

percentage of the expected sample capacity based on the active mass and theoretical capacity;

FIG. 3 is a graph showing voltage curves for cycle number 7, 107 and 207 of the cell with a  $\text{Li}_4\text{Ti}_5\text{O}_{12}$  cathode and a Lithium metal anode 110 °C with LiTFSI in  $\text{P}_{14}\text{TFSI}$  in the molar ration 0.38:0.62;

FIG. 4 is a graph showing charge and discharge capacity of the cell with a  $\text{Li}_4\text{Ti}_5\text{O}_{12}$  cathode and a Lithium metal anode 110 °C with 2.0 mol/kg LiTFSI in  $\text{P}_{16}\text{TFSI}$ . The capacity is given as percentage of the expected sample capacity based on the active mass and theoretical capacity;

FIG. 5 is a graph showing charge and discharge capacity of the cell with a  $\text{TiS}_2$  cathode and a Lithium metal anode 110 °C with LiTFSI in  $\text{P}_{14}\text{TFSI}$  in the molar ration 0.40:0.60. The capacity is given as percentage of the expected sample capacity based on the active mass and theoretical capacity;

FIG. 6 is a graph showing voltage curve for cycle 50 of the cell with a  $\text{TiS}_2$  cathode and a Lithium metal anode 110 °C with LiTFSI in  $\text{P}_{14}\text{TFSI}$  in the molar ration 0.40:0.60;

FIG. 7 is a graph showing charge and discharge capacity of the cell with a  $\text{Li}_4\text{Ti}_5\text{O}_{12}$  cathode and a Lithium metal anode 150 °C with LiTFSI in  $\text{P}_{44}\text{TFSI}$  in the molar ration 0.30:0.70. The capacity is given as percentage of the expected sample capacity based on the active mass and theoretical capacity;

FIG. 8 is a graph showing the potential curves of three cells with a  $\text{LiMn}_2\text{O}_4$  cathode and a Lithium metal anode. Cell A contains a reference electrolyte based on

organic solvents at 25 °C and shows the expected characteristic potential curve. Cells B and C contain pyrrolidinium based electrolytes at 110 °C and show failure of the cells starting; and

5        FIG. 9 shows the characteristic flat potential curve for  $\text{LiFePO}_4$  cathode and a Lithium metal anode 110 °C with LiTFSI in  $\text{P}_{14}\text{TFSI}$  in the molar ration 0.40:0.60. The potential is given as function of time.

#### DETAILED DESCRIPTION OF THE INVENTION

10        FIG.1A depicts that a pyrrolidinium compound comprises a positively charged ring structure of four carbon atoms and one nitrogen atom. The depicted compound has the formula:  $N\text{-R}_1\text{-N-R}_2\text{-pyrrolidinium}$ , wherein  $\text{R}_1$  and  $\text{R}_2$  are alkyl groups and wherein  $\text{R}_3\text{-R}_{10}$  are either: H; F; 15 separate alkyl groups which may be branched, substituted and comprise heteroatoms; separate phenyl groups which may be substituted and comprise heteroatoms. In the electrochemical element according to the invention is it preferred that  $\text{R}_1$  is methyl and  $\text{R}_2$  is butyl or hexyl or 20 that  $\text{R}_1=\text{R}_2$  is butyl.

FIG. 1B depicts the chemical structure of 1-butyl-1-methyl-pyrrolidinium and FIG.1C depicts the chemical structure of 1-butyl-2,2,3,3,4,4,5,5-octafluoro-1-methyl-pyrrolidinium.

25        Several rechargeable batteries with electrolytes comprising pyrrolidinium based ionic liquids were made and tested using the manufacturing and testing procedures that are described hereinbelow. Electrolytes were synthesised by mixing pyrrolidinium based ionic liquids 30 and lithium salts. The following acronyms will be used:

$\text{P}_{14}$ =1-methyl-1-butyl-pyrrolidinium

$\text{P}_{16}$ =1-methyl-1-hexyl-pyrrolidinium

P<sub>44</sub>=di-butyl-pyrrolidinium

TFSI=bis(trifluoromethylsulfonyl)imide= $N(CF_3SO_2)_2^-$

P<sub>14</sub>TFSI and P<sub>16</sub>TFSI (acquired from Merck KGaA) were dried under dynamic vacuum at 90 °C for 48 hours. The salts LiTFSI (LiN(CF<sub>3</sub>SO<sub>2</sub>)<sub>2</sub>, 3M) and Lithium-perchlorate (LiClO<sub>4</sub>, from Alfa Aesar) were dried under dynamic vacuum at 130 °C for 48 hour. After being dried, the materials were transferred into a helium filled glovebox (water content <5 ppm). The following electrolytes were made by mixing the appropriate amounts of ionic liquid and salt, resulting in clear and stable liquids:

5 mol% LiTFSI in P<sub>14</sub>TFSI

0.38 mol LiTFSI in 0.62 mol P<sub>14</sub>TFSI

0.40 mol LiTFSI in 0.60 mol P<sub>14</sub>TFSI

2.0 mol/kg LiTFSI in P<sub>16</sub>TFSI

1.0 mol/kg LiClO<sub>4</sub> in P<sub>14</sub>TFSI

0.30 mol LiTFSI in 0.70 mol P<sub>44</sub>TFSI

Electrodes were made of LiCrTiO<sub>4</sub>, Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub>, LiFePO<sub>4</sub> and TiS<sub>2</sub> and were coated as follows.

The electrodes were made by the doctor-blade technique on Aluminium or Copper foil current collectors using a paste of the active materials. The pastes contained typically 80 w% active material, 10-13 w% conductive additives, and 7-10 w% of a binder dissolved in 1-methyl-2-pyrrolidone (Merck KGaA). The conductive additives were a mixture of carbon black (2-10%, SuperP from MMM) and graphite (0-10 w%, KS4 from Timcal). The binder was either polyvinylidene fluoride (PVDF, from Solvay) or polymethylmethacrylate (PMMA). LiCrTiO<sub>4</sub> and LiFePO<sub>4</sub> were synthesised in house, Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> was obtained

from Hohsen Corporation Japan,  $\text{TiS}_2$  was obtained from Alfa Aesar,  $\text{LiMn}_2\text{O}_4$  was obtained from Sedema. The coatings were dried at 140 °C for about 15 minutes, densified using a Durston rolling mill, and further dried overnight under dynamic vacuum at 80 °C. Finally, samples of 15 mm diameter, with a typical capacity of 1-2 mAh, were punched out and used for testing.

All measurement were done using CR2320 type coincells (23 mm diameter, 2 mm high, 304 steel, acquired from Hohsen Corporation Japan), with polypropylene (PP) or polytetrafluoroethylene (PTFE) gaskets, or in 304 steel cells with high temperature viton O-rings. All cells were assembled in a glovebox. Typically, a cell was made by stacking in a can: an electrode, a 21 mm diameter glassfiber mat (type GF/C, Whatman), a gasket, 4-5 drops of electrolyte with a 1 ml polyethylene pipet, a 17 mm diameter Lithium disk 0.38 mm thick (Chemetall), a 17 mm diameter pressing plate 0.2 mm thick, a 15 mm diameter wave-spring, and a cap which was insulated by tape. If necessary, the electrolyte was warmed to about 100 °C to reduce the viscosity. The cells were closed in a manual CR2320 crimping tool (Hohsen Corporation Japan).

#### Testing of batteries

The cells were cycled (subsequent charging and discharging) in air in climate chambers ( $\pm 0.1$  °C accuracy) using Maccor S4000 battery testers. The cells were subjected to various current densities, ranging from 0.1 to 1.0 C-rate. Within a cycle the current was constant and equal for discharging and charging. The 1 C-rate is here defined as the current needed to fully discharge the battery in 1 hour as calculated from the mass of active material and its specific storage

capacity. Thus, ideally a 0.1C-rate discharge lasts for 10 hours and a 2.0 C-rate lasts 0.5 hour.

EXAMPLE I:

5 "Testing at 110° of a rechargeable battery with a  
Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> cathode, a Lithium metal anode and an  
electrolyte comprising LiTFSI in P<sub>14</sub>TFSI"

A coincell was made according to the procedures described above. Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> was used as the cathode material with PvdF as binder on an Aluminium current  
10 collector. The electrolyte was a mixture of LiTFSI dissolved in P<sub>14</sub>TFSI in the molar ratio of 0.38:0.62. The cell was cycled 242 times between 1.0 and 2.0 V at 110 °C.

In the first 29 cycles the current was varied between  
15 0.1 and 1.0 °C. FIG. 2 shows the capacity for discharging and charging as percentage of the expected sample capacity. Very stable cycling behaviour of the battery was found with good rate capability and high efficiency. The voltage curves in FIG. 3 show the typical voltage  
20 curve of Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> versus lithium for the 7-th, 107-th and 207-th cycle for the same current density indicating that the active material did not change and did not loose its integrity.

EXAMPLE II:

25 "Testing at 110 °C of a rechargeable battery with a  
Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> cathode, a Lithium metal anode and an  
electrolyte comprising LiTFSI in P<sub>16</sub>TFSI"

A coincell was made according to the procedures described above. Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> was used as the cathode  
30 material with PvdF as binder on an Aluminium current collector. The electrolyte was a 2.0 mol/kg mixture of

LiTFSI dissolved in P<sub>16</sub>TFSI. The cell was cycled 150 times between 1.0 and 2.0 V at 110 °C.

In the first 29 cycles the current was varied between 0.1 and 1.0 °C. FIG. 4 shows the capacity for discharging and charging as percentage of the expected sample capacity. Very stable cycling behaviour of the battery was found with good rate capability and high efficiency.

EXAMPLE III:

"Testing at 110 °C of a rechargeable battery with a TiS<sub>2</sub> cathode, a Lithium metal anode and an electrolyte comprising LiTFSI in P<sub>14</sub>TFSI"

A coin cell was made according to the procedures described above. TiS<sub>2</sub> was used as the cathode material with PvdF as binder on an Aluminium current collector. The electrolyte was a mixture of LiTFSI dissolved in P<sub>14</sub>TFSI in the molar ratio of 0.40:0.60. The cell was cycled 13 times between 1.8 and 2.5 V and 87 times between 1.5 and 2.5 V at 110 °C.

FIG. 5 shows the capacity for discharging and charging as percentage of the expected sample capacity. The lowering of the lower cut-off voltage increased the capacity substantially. Apart from some initial fading the cycling is fairly stable and with high efficiency. The voltage curves in FIG. 6 shows the typical voltage curve of TiS<sub>2</sub> versus lithium for the 50-th cycle.

EXAMPLE IV:

"Testing at 150 °C of a rechargeable battery with a Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> cathode, a Lithium metal anode and an electrolyte comprising LiTFSI in P<sub>44</sub>TFSI"

A coin cell was made according to the procedures described above. Li<sub>4</sub>Ti<sub>5</sub>O<sub>12</sub> was used as the cathode material with PvdF as binder on an Aluminium current

collector. The electrolyte was a mixture of LiTFSI dissolved in P<sub>44</sub>TFSI (di-butyl-pyrrolidinium-TFSI) in the molar ratio 0.30:0.70. The cell was cycled 60 times between 1.0 and 2.0 V at 150 °C. The current was varied between a 0.1, 0.5, and 1.0C-rate.

FIG. 7 shows the capacity for discharging and charging as percentage of the expected sample capacity. Even at 150 °C the cycling stability is very good and similar to that at 110 °C demonstrating the use of these electrolytes in high temperature batteries.

EXAMPLE V:

"Testing at 110 °C of a rechargeable battery with a 4.1 V LiMn<sub>2</sub>O<sub>4</sub> cathode, a Lithium metal anode and an electrolyte comprising LiTFSI in P<sub>14</sub>TFSI or P<sub>16</sub>TFSI"

Three coincells were made according to the procedures described above. LiMn<sub>2</sub>O<sub>4</sub> was used as the cathode material with PvdF as binder on a 304-steel current collector. The electrolytes were:

A. 1 M LiPF<sub>6</sub> in EC/DMC 2:1 w/w;

B. 0.05 mol LiTFSI dissolved in 0.95 mol P<sub>14</sub>TFSI

C. 1 mol/kg LiTFSI dissolved in P<sub>16</sub>TFSI

The cells were charged and discharged between 3.5 and 4.3 V at 25 °C for electrolyte A and at 110 °C for electrolyte B and C. The current was a 0.1C-rate.

FIG. 8 shows the potential curves for the three cells. The reference cell with electrolyte A shows the expected characteristic potential curve for LiMn<sub>2</sub>O<sub>4</sub> being symmetrical in charge and discharge. The cell with electrolyte B did not reach a potential higher than 4 V and failed. The cell with electrolyte C showed a too small charge capacity and an even smaller discharge



capacity. The specific  $\text{LiMn}_2\text{O}_4$  potential curve is lost and the capacity faded quickly. These tests demonstrate that the pyrrolidinium based electrolytes cannot be used with intercalation materials which have an upper reversible-potential-limit higher than 4 V versus  $\text{Li}/\text{Li}^+$ .

EXAMPLE VI:

"Testing at 110 °C of a rechargeable battery with a 3.4 V  $\text{LiFePO}_4$  cathode, a Lithium metal anode and an electrolyte comprising  $\text{LiTFSI}$  in  $\text{P}_{14}\text{TFSI}$ "

A coin cell was made according to the procedures described above.  $\text{LiFePO}_4$  was used as the cathode material with PvdF as binder on an Aluminium current collector. The electrolyte was a mixture of  $\text{LiTFSI}$  dissolved in  $\text{P}_{14}\text{TFSI}$  in the molar ratio 0.40:0.60. The cell was cycled between 3.0 and 3.8 V as the upper cut-off potential at 110 °C. The current was a 0.1C-rate.

FIG. 9 shows the characteristic flat potential curve for  $\text{LiFePO}_4$ , being symmetrical for charge and discharge. This tests demonstrates that the pyrrolidinium based electrolytes can be used with intercalation materials with an upper reversible-potential-limit up to 4 V versus  $\text{Li}/\text{Li}^+$ .

EXAMPLES I-VI and FIG. 1-9 demonstrate that the tested cells with pyrrolidinium based ionic liquid electrolytes and with a cathode comprising an intercalation material having an upper reversible-potential-limit ( $\text{RPL}_{\text{upp}}$ ) of at most 4 V versus  $\text{Li}/\text{Li}^+$  are suitable for use as rechargeable batteries at a high temperature of up to at least 150 °C.

The examples further indicate that suitable materials for use in the rechargeable batteries are:

-  $\text{Li}_4\text{Ti}_5\text{O}_{12}$ ,  $\text{Li}_4\text{Mn}_5\text{O}_{12}$ ,  $\text{LiCrTiO}_4$ , and  $\text{TiS}_2$  as active intercalation materials.

It is also believed that other known intercalation materials as for example  $\text{Li}_{1+y}\text{Mn}_{2-y}\text{O}_4$  (~2.9 V insertion,  $0 \leq y \leq 1/3$ ),  $\text{LiMg}_y\text{Ni}_{0.5-y}\text{Mn}_{1.5}\text{O}_4$  (~2.9 V insertion,  $0 \leq y \leq 0.5$ ),  $\text{Li}_2\text{Mn}_4\text{O}_9$  (~2.9 V insertion),  $\text{Li}_7\text{MnN}_4$ , and  $\text{Li}_3\text{FeN}_2$  can be used.

- Aluminium and stainless steel SUS304 as a current collector materials.

It is also believed that other materials as for example Nickel, Copper, Gold, Platinum, Carbon, and Graphite can be used as current collectors.

- PvdF and PMMA as binder materials.

It is also believed that other known binder materials as for example PTFE, PCTFE, ECTFE, ETFE, and FEP can be suitable binder materials.

- Carbon black and graphite as conductive additives.

It is also believed that instead or together with Carbon black and Graphite it is possible to use a metal foam or similar porous but electronically conductive structure, glassy carbon, or a metal powder as a conductive matrix in the electrodes. This can be an advantage in case Carbon black and/or graphite cause unwanted side reactions with other materials in the battery.

- porous glassfiber mat as separator material.


It is also believed that for example porous layers comprising  $\text{Al}_2\text{O}_3$ , MgO, Li- $\beta$ -Alumina are suitable separator materials.

Mixtures of  $\text{P}_{14}\text{TFSI}$ ,  $\text{P}_{16}\text{TFSI}$  and  $\text{P}_{44}\text{TFSI}$  with  $\text{LiTFSI}$  and/or  $\text{LiClO}_4$ .

C L A I M S

1. An electrochemical element with a cathode, an anode and an electrolyte arranged between the cathode and anode, which electrolyte comprises an ionic liquid comprising an anion and a cation, which cation has a pyrrolidinium ring structure,  
5 and wherein the active material of the cathode comprises an intercalation material having an upper reversible-potential-limit of at most 4 V versus Li/Li<sup>+</sup>.
2. The electrochemical element of claim 1, wherein the  
10 electrochemical element is a primary battery or a rechargeable battery or an electrochemical capacitor.
3. The electrochemical element of claim 1 or 2, wherein the electrochemical element is configured for use at a temperature above 50 °C.
- 15 4. The electrochemical element of claim 3, wherein the electrochemical element is configured for use at a temperature between 60 and 200 °C.
5. The electrochemical element of any preceding claim, wherein the pyrrolidinium ring structure has the formula:  
20  $N-R_1-N-R_2$ -pyrrolidinium, wherein  $R_1$  and  $R_2$  are alkyl groups.
6. The electrochemical element of claim 5, wherein the pyrrolidinium ring structure has the formula  $N$ -methyl- $N$ -butyl-pyrrolidinium.
- 25 7. The electrochemical element claim 5, wherein the pyrrolidinium ring structure has the formula  $N$ -methyl- $N$ -hexyl-pyrrolidinium.

8. The electrochemical element of claim 1, wherein the pyrrolidinium structure is:



wherein R<sub>1</sub>-R<sub>10</sub> are either: H; F; separate alkyl groups which may be branched, substituted and comprise heteroatoms; separate phenyl groups which may be substituted and comprise heteroatoms.

9. The electrochemical element of any preceding claim, wherein the anion of the ionic liquid comprises any of the following compounds:

ClO<sub>4</sub><sup>-</sup>, PF<sub>6</sub><sup>-</sup>, BF<sub>4</sub><sup>-</sup>, AsF<sub>6</sub><sup>-</sup>, a halogen ion, N(CF<sub>3</sub>)<sub>2</sub><sup>-</sup>, N(CF<sub>3</sub>SO<sub>2</sub>)<sub>2</sub><sup>-</sup>, CF<sub>3</sub>SO<sub>3</sub><sup>-</sup>, N(CH<sub>3</sub>SO<sub>2</sub>)<sub>2</sub><sup>-</sup>, N(C<sub>2</sub>F<sub>5</sub>SO<sub>2</sub>)<sub>2</sub><sup>-</sup>, B(C<sub>2</sub>O<sub>4</sub>)<sub>2</sub><sup>-</sup>, C(CF<sub>3</sub>SO<sub>2</sub>)<sub>3</sub><sup>-</sup>.

10. The electrochemical element of claim 1, wherein the electrolyte further comprises a salt.

11. The electrochemical element of claim 10, wherein the salt comprises an alkali salt, particularly a Lithium salt, more particularly a Lithium salt comprising any of the following compounds:

- LiN(CF<sub>3</sub>SO<sub>2</sub>)<sub>2</sub>, LiCF<sub>3</sub>SO<sub>3</sub>, LiClO<sub>4</sub>, LiBF<sub>4</sub>, LiPF<sub>6</sub>, or LiAsF<sub>6</sub>, LiB(C<sub>2</sub>O<sub>4</sub>)<sub>2</sub>, LiC(CF<sub>3</sub>SO<sub>2</sub>)<sub>3</sub>.

12. The electrochemical element of claim 10, wherein the salt comprises MgCF<sub>3</sub>SO<sub>2</sub> or Mg(ClO<sub>4</sub>)<sub>2</sub>.

13. The electrochemical element of any preceding claim, wherein the active material of the cathode comprises an intercalation material as the major constituent by mass.

14. The electrochemical element of claim 13, wherein the cathode comprises as the major constituent by mass of the active material any of the following compounds:

$\text{Li}_4\text{Ti}_5\text{O}_{12}$ ,  $\text{LiTi}_2\text{O}_4$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ),  $\text{V}_2\text{O}_5$ ,  $\text{Li}_4\text{Mn}_5\text{O}_{12}$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Mn}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ).

15. The electrochemical element of claim 13, wherein the cathode comprises  $\text{LiCrTiO}_4$  as the major constituent by mass of the active material.

16. The electrochemical element of claim 13, wherein the cathode comprises  $\text{TiS}_2$  as the major constituent by mass of the active material.

17. The electrochemical element of claim 13, wherein the cathode comprises  $\text{Li}_{1-y}\text{M}_y\text{FePO}_4$ , where  $\text{M}=\text{Mg}$ ,  $\text{Nb}$ ,  $\text{Zr}$ ,  $\text{Ti}$ ,  $\text{Al}$  and ( $0 \leq y \leq 0.02$ ), as the major constituent by mass of the active material.

18. The electrochemical element of claim 1, wherein the anode comprises Lithium metal as the major constituent by mass of the active material.

19. The electrochemical element of claim 1, wherein the anode comprises as the major constituent by mass of the active material any of the following compounds:

$\text{Li}_4\text{Ti}_5\text{O}_{12}$ ,  $\text{LiCrTiO}_4$ ,  $\text{LiTi}_2\text{O}_4$ ,  $\text{Li}_{4-y}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq y \leq 1$ ).

20. The electrochemical element of claim 1, wherein the cathode comprises as the major constituent by mass of the active material  $\text{Li}_{1-a}\text{FePO}_4$  ( $0 \leq a \leq 1$ ) and wherein the anode comprises as the major constituent by mass of the active material  $\text{Li}_{(4-y)+b}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq b \leq 3$  and ( $0 \leq y \leq 1$ )).

21. The electrochemical element of claim 1, wherein the cathode comprises as the major constituent by mass of the

active material  $\text{Li}_{(4-y)+a}\text{Mg}_y\text{Mn}_5\text{O}_{12}$  ( $0 \leq a \leq 1$  and  $0 \leq y \leq 1$ ) and wherein the anode comprises as the major constituent by mass of the active material  $\text{Li}_{(4-y)+b}\text{Mg}_y\text{Ti}_5\text{O}_{12}$  ( $0 \leq b \leq 3$  and  $0 \leq y \leq 1$ ).

5 22. The electrochemical element of claim 1, wherein the cathode and/or anode comprises polyvinylidene fluoride (PVDF) as a binder material.


23. The electrochemical element of claim 1, wherein the cathode and/or anode comprises polytetrafluoroethylene  
10 (PTFE) as a binder material.

24. A method of providing electrical energy in an underground wellbore, wherein the energy is provided by an electrochemical element according to any preceding claim.

15 25. The method of claim 24, wherein the wellbore forms part of an oil and/or gas production well or a geothermal well.


26. The method of claim 24, wherein the wellbore forms part of an oil and/or gas production well and oil and/or  
20 gas is produced through the well and wherein the flow of oil and/or gas is monitored and/or controlled by electric downhole monitoring and/or control equipment which is powered by an electrochemical element according to any one of claims 1-23.

Fig.1A. Pyrrolidinium cations




pyrrolidinium ring structure:  
R<sub>1</sub>-R<sub>10</sub> is e.g. H, F, alkylgroup, etc.

Fig.1B.



1-butyl-1-methylpyrrolidinium

Fig.1C.



1-butyl-2,2,3,3,4,4,5,5-octafluoro-1-methylpyrrolidinium




FIG 2






FIG 3




FIG 4




FIG 5




FIG 6




FIG 7




FIG 8




FIG 9

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP2004/053182

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01M10/40 H01M10/39 H01M10/36 H01M6/14 H01M6/16  
H01G9/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M H01G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 01/15258 A (MONASH UNIVERSITY; MACFARLANE, DOUGLAS, ROBERT; FORSYTH, MARIA; HUANG,) 1 March 2001 (2001-03-01) cited in the application	1-26
A	MACFARLANE D R ET AL: "Pyrrolidinium imides: a new family of molten salts and conductive plastic crystal phases" 20 May 1999 (1999-05-20), JOURNAL OF PHYSICAL CHEMISTRY. B, MATERIALS, SURFACES, INTERFACES AND BIOPHYSICAL, WASHINGTON, DC, US, PAGE(S) 4164-4170 , XP002211103 ISSN: 1089-5647 cited in the application	1-26
A	US 2002/055045 A1 (MICHOT CHRISTOPHE ET AL) 9 May 2002 (2002-05-09)	1-26

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*Z\* document member of the same patent family

Date of the actual completion of the international search

18 February 2005

Date of mailing of the international search report

11/03/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Götz, H



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP2004/053182

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0115258	A	01-03-2001	AU 6720800 A	19-03-2001
			WO 0115258 A1	01-03-2001
US 2002055045	A1	09-05-2002	CA 2228801 A1	03-08-1999
			CA 2256945 A1	18-06-2000
			CA 2279399 A1	10-06-1999
			CA 2283670 A1	12-08-1999
			WO 9940025 A1	12-08-1999
			EP 0968181 A1	05-01-2000
			EP 0971854 A1	19-01-2000
			WO 9928292 A1	10-06-1999
			JP 2002500678 T	08-01-2002
			JP 2001527505 T	25-12-2001
			US 6620546 B1	16-09-2003
			US 6365301 B1	02-04-2002
			US 2002009635 A1	24-01-2002

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKÉWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**